

# **Specification for PVC Lined Steel Tubular Goods**

API SPECIFICATION 15LT (SPEC 15LT)  
FIRST EDITION, JANUARY 1, 1993

**American Petroleum Institute**  
1220 L Street, Northwest  
Washington, DC 20005



**Issued by  
AMERICAN PETROLEUM INSTITUTE  
Production Department**

FOR INFORMATION CONCERNING TECHNICAL CONTENTS OF  
THIS PUBLICATION CONTACT THE API PRODUCTION DEPARTMENT,  
1201 MAIN STREET, SUITE 2535, DALLAS, TX 75202-3904 — (214) 748-3841.  
SEE BACK COVER FOR INFORMATION CONCERNING HOW TO OBTAIN  
ADDITIONAL COPIES OF THIS PUBLICATION.

Users of this publication should become familiar with its scope  
and content, including any provisions it may have regarding marking of  
manufactured products. This publication is intended to supplement rather  
than replace individual engineering judgment.

OFFICIAL PUBLICATION



REG. U.S. PATENT OFFICE

Copyright © 1992 American Petroleum Institute

## TABLE OF CONTENTS

Policy .....	3
Foreword .....	4
Suggestions for Ordering .....	5
Section 1: Scope .....	7
Section 2: Glossary & Definitions .....	8
Section 3: Process of Manufacture .....	9
Section 4: Material Composition .....	11
Section 5: Physical Properties, Test & Requirements .....	12
Section 6: End Protection .....	14
Section 7: Couplings .....	14
Section 8: Inspection .....	14
Section 9: Marking .....	16
Section 10: Record Retention Requirements .....	16
Appendix A: Recommended Chemical Resistance Table .....	17
Appendix B: Use of API Monogram .....	21
Appendix C: Reference Standards .....	22
Appendix D: Metric Conversions .....	23
Appendix E: Purchaser Inspection .....	24

**Attention Users of this Publication:** Portions of this publication have been changed from the previous edition. The location of changes has been marked with a bar in the margin. In some cases the changes are significant, while in other cases the changes reflect minor editorial adjustments. The bar notations in the margins are provided as an aid to users to identify those parts of this publication that have been changed from the previous edition, but API makes no warranty as to the accuracy of such bar notations.

*Requests for premission to reproduce or translate all or any part of the material published herein should be addressed to the Director, American Petroleum Institute, Production Department, 1201 Main Street, Suite 2535, Dallas TX 75202-3904.*

## POLICY

1. API PUBLICATIONS NECESSARILY ADDRESSES PROBLEMS OF A GENERAL NATURE. WITH RESPECT TO PARTICULAR CIRCUMSTANCES, LOCAL STATE AND FEDERAL LAWS AND REGULATIONS SHOULD BE REVIEWED.

2. API IS NOT UNDERTAKING TO MEET DUTIES OF EMPLOYERS, MANUFACTURERS OR SUPPLIERS TO WARN AND PROPERLY TRAIN AND EQUIP THEIR EMPLOYEES AND OTHERS EXPOSED, CONCERNING HEALTH AND SAFETY RISKS AND PRECAUTIONS, NOR UNDERTAKING THEIR OBLIGATIONS UNDER LOCAL, STATE OR FEDERAL LAWS.

3. INFORMATION CONCERNING SAFETY AND HEALTH RISKS AND PROPER PRECAUTIONS WITH RESPECT TO PARTICULAR MATERIALS AND CONDITIONS SHOULD BE OBTAINED FROM THE EMPLOYER. THE MANUFACTURER OR SUPPLIER OF THAT MATERIAL, OR THE MATERIAL SAFETY DATA SHEET.

4. NOTHING CONTAINED IN ANY API PUBLICATION IS TO BE CONSTRUCTED AS GRANTING ANY RIGHT, BY IMPLICATION OR OTHERWISE, FOR

THE MANUFACTURE, SALE OR USE OF ANY METHOD, APPARATUS, OR PRODUCT COVERED BY LETTERS PATENT. NEITHER SHOULD ANYTHING CONTAINED IN THE PUBLICATION BE CONSTRUED AS INSURING ANYONE AGAINST LIABILITY FOR INFRINGEMENT OF LETTERS PATENT.

5. GENERALLY, API STANDARDS ARE REVIEWED AND REVISED REAFFIRMED, OR WITHDRAWN AT LEAST EVERY FIVE YEARS. SOMETIMES A ONE-TIME EXTENSION OF UP TO TWO YEARS WILL BE ADDED TO THIS REVIEW CYCLE. THIS PUBLICATION WILL NO LONGER BE IN EFFECT FIVE YEARS AFTER IT'S PUBLICATION DATE AS AN OPERATIVE API STANDARD OR, WHERE AN EXTENSION HAS BEEN GRANTED, UPON REPUBLICATION. STATUS OF THE PUBLICATION CAN BE ASCERTAINED FROM THE API AUTHORIZING DEPARTMENT (TEL. (214) 220-9111). A CATALOG OF API PUBLICATIONS AND MATERIALS IS PUBLISHED ANNUALLY AND UPDATED QUARTERLY BY API, 1220 L. STREET, N.W., WASHINGTON, D.C. 20005.

## FOREWORD

### Purpose Statement

a. The purpose of this Specification is to provide standards for PVC lined steel pipe or tubing, suitable for use in conveying water and/or oil in the Petroleum Industry.

b. American Petroleum Institute (API) Specifications are published as aids to the procurement of standardized equipment and materials, as well as instructions to manufacturers of equipment or materials covered by an API Specification. These Specifications are not intended to obviate the need for sound engineering, nor to inhibit in any way anyone from purchasing or producing products to other specifications.

c. The formulation and publication of API Specifications and the API monogram program is not intended in any way to inhibit the purchase of products from companies not licensed to use the API monogram.

d. API Specifications may be used by anyone desiring to do so, and diligent effort has been made by the Institute to assure the accuracy and reliability of the data contained therein. However, the Institute makes no rep-

resentation, warranty, or guarantee in connection with the publication of any API Specification and hereby expressly disclaims any liability or responsibility for losses or damage resulting from their use, for any violation of any federal, state or municipal regulation with which an API Specification may conflict, or for the infringement of any patent resulting from the use of an API Specification.

e. Any Manufacturer marking equipment or materials in conformance with the marking requirements of an API Specification is solely responsible for complying with all the applicable requirements of that Specification. The American Petroleum Institute does not represent, warrant or guarantee that such products do in fact conform to the applicable API Specification.

f. This Specification for PVC lined steel tubular goods was formulated by the API Production Department Committee on Standardization of Plastic Pipe.

g. This Standard (supplement) shall become effective on the date printed on the cover but may be used voluntarily from the date of distribution.

**SUGGESTIONS FOR ORDERING****SUGGESTIONS FOR ORDERING API PVC LINED STEEL LINE PIPE**

In placing orders for PVC Lined Steel Line Pipe to be manufactured in accordance with API Specification 15LT, the purchaser should specify the following on the purchase order:

Specifications .....	API Specification 15LT
Quantity .....	
Steel Pipe Grade or Class .....	API Specification 5L, Table 3.1 & 4.1
New Steel Pipe Furnished by Purchaser .....	
Used Steel Pipe Furnished by Purchaser .....	
New Steel Pipe Furnished by Manufacturer .....	
Process of Pipe Manufacture .....	API Specification 5L, Table 2.1
Size Nominal .....	
Weight per Foot or Wall Thickness .....	
Length .....	
Inspection of Pipe by Purchaser .....	Section 8
Fittings .....	Paragraph 7.2
PVC Liner Class .....	API Specification 15LT, Paragraph 4.1
Size Nominal .....	Table 5.2
SDR or Wall Thickness .....	Table 5.1, 5.2
End Protection .....	Section 6
Rejection of PVC Liner .....	Paragraph 5.1.g

**Delivery Date & Shipping Instructions**

Attention is called to the following stipulations which are subject to agreement between the purchaser and the manufacturer:

Hydrostatic Tests and Frequency .....	Paragraph 3.2.a
End Protection .....	Section 6
Inspection .....	Section 8
Marking Requirements .....	Section 9 & Appendix B
Rejection of Steel Tubular .....	Paragraph 3.2.h
Acceptance .....	Appendix E
Testing .....	Section 5

**SPECIAL NOTE:**

Nothing in this specification should be interpreted as indicating a preference by the Committee for any material or process or as indicating equality between the various materials or processes. In the selection of materials and processes, the purchaser must be guided by his experience and by the service for which the PVC lined steel pipe is intended.

**SUGGESTIONS FOR ORDERING API PVC LINED STEEL TUBING**

In placing orders for PVC Lined Steel Tubing to be manufactured in accordance with API Specification 15LT, the purchaser should specify the following on the purchase order:

Specification .....	API Specification 15LT
Quantity .....	
Type of Tubing .....	API Specification 5CT Per Table 2.1
Non-Upset, External-Upset or Integral Joint .....	
Threaded, Plain-End or Special End .....	
With or Without Couplings .....	
Special Bevel Couplings .....	
Special-Clearance Couplings .....	
New Steel Tubing Furnished by Purchaser .....	
Used Steel Tubing Furnished by Purchaser .....	
New Steel Tubing Furnished by Manufacturer .....	
Used Steel Tubing Furnished by Manufacturer .....	
Size (outside diameter) .....	
Weight per foot or Wall Thickness .....	
Grade .....	
Range Length .....	
Inspection of Tubing by Purchaser .....	Section 8
PVC Liner Class .....	API Specification 15LT Paragraph 4.1
Size Nominal .....	Table 5.3
SDR or Wall Thickness .....	Table 5.1, 5.3
End Protection .....	Section 6
Rejection of PVC Liner .....	Paragraph 5.1.g

**Delivery Date & Shipping Instructions**

Attention is called to the following stipulations which are subject to agreement between the purchaser and the manufacturer:

Coupling Make-Up (Other than power-tight) .....	API Specification 5CT
Tubing with Couplings Detached .....	API Specification 5CT
Hydrostatic Tests and Frequency .....	Paragraph 3.2.a
End Protection .....	Section 6
Inspection .....	Section 8
Marking Requirements .....	Section 9 & Appendix B
Rejection of Steel Tubular .....	Paragraph 3.2.h
Acceptance .....	Appendix E
Testing .....	Section 5

**SPECIAL NOTE:**

Nothing in this specification should be interpreted as indicating a preference by the Committee for any material or process or as indicating equality between the various materials or processes. In the selection of materials and processes, the purchaser must be guided by his experience and by the service for which the PVC lined steel tubing is intended.

## SECTION 1 SCOPE

### 1.1 COVERAGE

a. This specification covers PVC lined steel line pipe and tubing. Dimensions, materials and physical properties are included.

b. Technical content provides requirements for performance, materials, dimensions and weight; test and inspection; marking and storing.

*NOTE 1: PVC lined accessories and fittings are available, but are beyond the scope of this specification. Consult the appropriate manufacturer regarding PVC lined accessories and fittings.*

*NOTE 2: Mortars and/or adhesives may be used in the fabrication of PVC lined steel line pipe and tubing.*

### 1.2 APPLICATIONS

a. **PRODUCTS.** These specifications apply to polyvinyl chloride (PVC) lining of steel line pipe and tubing used as a barrier for shielding the steel from corrosion attack in the handling of oilfield fluids. Specific products covered by the specification are listed as follows:

1. Line Pipe
2. Tubing

b. **SERVICE LIMITATIONS.** The standard service conditions are as follows:

- Service temperature is 150°F maximum.
- Use of products covered by this specification should be limited to published industry data in the absence of tests for specific applications. A recommended chemical

resistance table (Appendix A) lists general resistances to many specific chemical compounds at 0 psig for 72°F and 140°F. It is suggested tests be conducted for special pressure/temperature and multi-phase conditions.

- Gases under elevated pressure service conditions are not recommended.

- Special attention should be made toward, but not limited to certain aromatic chemicals, such as benzene, toluene, xylene and ketones.

**1.3 GENERAL.** This specification includes by reference, either in total or in part, other API, industry, and government standards listed in Appendix C.

a. **REQUIREMENTS.** Requirements of other standards included by references in this Specification are essential to the safety and of the equipment produced within a given system.

b. **EQUIVALENT STANDARDS.** Other nationally or internationally recognized standards shall be submitted to and approved by the API Committee on Standardization of Plastic Pipe for inclusion in this Specification prior to use as equivalent standards.

**1.4 UNIT CONVERSIONS.** U. S. Customary units are in all cases preferential and shall be the standard in this Specification. Nominal sizes will continue to be shown as fractions. For the purposes of this Specification the fractions and their decimal equivalents are equal and interchangeable. Metric conversions are described in Appendix D.



## SECTION 2

### GLOSSARY (ABBREVIATIONS, DEFINITIONS)

#### 2.1 ABBREVIATIONS

**API** — American Petroleum Institute

**ASTM** — American Society of Testing and Materials

#### 2.2 DEFINITIONS

**Acceptance Criteria** — Defined limits placed on characteristics of material, product or service.

**Adaptors** — Appurtenance that allows connecting components with different joining features.

**Change-over** — Interchangeability between liner systems.

**Compounder** — An entity which houses equipment to add and blend stabilizers, lubricants, pigments and other necessary ingredients with PVC resins to facilitate extrusion. Compounder can be PVC resin manufacturer, pipe extruder or a separate company.

**Date of Manufacture** — Manufacturers finished product date (month, year).

**Extruder** — An entity which converts PVC resin (PVC compounds) into pipe.

**Fittings** — Tees, 90's, 45's, Reducers, Flanges and Adaptors, and other accessories.

**Manufacturer** — An entity that fabricates or assembles the components to provide finished products.

**Manufacturer's batch or lot** — Quantity as determined by manufacturer for use in establishing traceability.

**May** — term used to indicate that a provision is optional.

**PVC Resin Manufacturer** — An entity that converts (polymerizes) vinyl chloride monomer into polyvinyl chloride (PVC) resins.

**Records** — Retrievable information.

**Schedule** — a pipe size system (outside diameters and wall thickness) originated by the iron pipe industry.

**Shall** — term used to indicate that a provision is mandatory.

**Should** — term used to indicate that a provision is not mandatory, but recommended as good practice.

**Standard Dimension Ratio (SDR)** — specific ratio of the average specific outside diameter (O.D.) to the minimum specific wall thickness.

**Steel Line Pipe** — Pipe used for other than down hole application.

**Visual Examination** — Examination of parts and equipment for visible defects in material and workmanship.

## SECTION 3 PROCESS OF MANUFACTURE

### 3.1 EXTRUSION PROCESS

#### a. EXTRUSION — THE MACHINES

**Single Screw Extrusion** — Favorable results of single screw extrusion with rigid PVC powder (dry blend) or PVC pellets rely on several basic but essential operations in the extrusion process. Promoting shear helps assure a competent level of work or energy in the compound which makes certain there is proper fusion, a homogeneous melt, and assures acceptable physical properties have been obtained. The shear is accomplished by running the extruder at high RPM and high compression (back pressure).

In the single screw process, generally PVC compounds can be handled for length/diameter (L/D) ratios of at least 24:1, and may differ in some operations. PVC extruders typically use a vacuum vent for extraction of volatiles (air pockets or gas filled voids). Common working pressure at the vent section have a range of 15-22 inches Hg vacuum. PVC single screws incorporate a two-stage screw design; a mixing zone and a decompression zone at the vented area. The screw also is designed with a hollow center for oil temperature control to assist in proper compound mix.

**Twin Screw Extrusion** — To achieve the best results in twin screw extrusion, low RPM along with low compression are necessary, just the opposite of single screw. This in turn creates very low friction (shear) for a considerable lower running temperature as well as a more consistent melt flow.

In the twin screw process L/D ratio is generally not considered due to the flexibility of compounds used (less heat sensitive). Similar to the single screw process, the twin screw process also uses a vacuum vent for extraction of volatiles. Typical working pressure for the vent section is 15-22 inches Hg vacuum. PVC twin screws differ slightly in design between machines, but basically have a feeding zone, decompression zone (at the vent section) and a mixing zone. The screws are each hollow centered for oil temperature control.

#### b. BASIC EXTRUSION OPERATION

In both operations, the compound enters the feed section and is carried by the screw(s) through the barrel. The heated PVC material is forced through a small hole or orifice (approximately 3/4"-1" diameter) and flows through a die. The die assists in giving the I.D. and O.D. a smooth glossy appearance. The material moves into the sizing tank, the cooling tank, and is pulled through the cooling tank by the take-off or pull-off which has a two-fold function. The pull-off helps pull the extruded material (soon to be finished product) through the cooling tanks and also controls the thickness of the wall by varying the speed. The finished product passes through a cutoff saw which is triggered by a microswitch for the desired length.

### 3.2. PRELIMINARY INSPECTIONS.

a. Steel tubular goods shall be adjudged suitable for lining by the manufacturer provided the following minimum requirements have been met:

Unless previously waived in writing by the purchaser, each length to be lined shall be hydrostatic tested with test pressure and duration subject to agreement between purchaser and manufacturer. If no waiver or agreement is addressed between such parties, a minimum five second test duration shall be used.

b. Steel tubular goods should be adjudged suitable for lining by the manufacturer provided the following minimum requirements have been met:

1. The maximum out-of-roundness should not exceed the manufacturer's acceptable limits.
2. The steel tubular goods should have no deviation from straightness exceeding the manufacturer's acceptable limits.
3. Pin and coupling threads on threaded and coupled pipe should be visually inspected for pulled, galled, or otherwise damaged threads. Tubular goods with thread wear exceeding manufacturer's acceptable limits should not be lined without reconditioning to meet these limits.
4. Tubular exteriors should be visually inspected for obvious defects such as crushed, pitted or corrosion damaged body. Missing, damaged, beveled, or special clearance couplings should be noted.
5. Tubular exteriors should be visually inspected for obvious pitting or corrosion damage, paraffin or other buildup, and existing coatings or linings.
6. Preliminary cleaning requirements should be determined. Tubular goods may require steaming, mechanical boring or pressure water blasting to prepare the interior surface for the grit blasting process, refer Table 8.1.
7. Steel tubular goods which have been determined unsuitable for lining should be marked and set aside at the manufacturer's facility. The purchaser should be notified for removal or disposal of the rejected steel tubulars.

**3.3 MANUFACTURING PROCESS.** PVC linings can be applied to new or used steel pipe and tubing. There are several types of manufacturing processes for inserting PVC liner systems. Currently, lining processes A, B, and C are different and not intended to be interchangeable. Consult the appropriate manufacturer if change-over capability is desired.

Lining processes may involve heating and forming of the PVC liner. Heating and forming procedures should be controlled to avoid degrading the corrosion resistance and mechanical properties of the PVC. The processes do not involve temperatures above 525°F (to prevent metallurgical damage — see API RP5L7) nor internal pressures exceeding specified minimum yield strength of the steel (per API Specs 5CT or 5L).

The most important criteria for the PVC liner is to serve as a continuous corrosion barrier. Once installed, the mechanical properties of the PVC liner do not add significantly to the system strength.

**a. FABRICATION PROCESS "A"**

A process of manufacturing in which a PVC tube or liner is inserted into a steel tube and bonded to the ID of that tube to create a corrosion barrier.

Steel line pipe or tubing, new or used, can be used in this lining process. The tubing is sandblasted on the ID to remove foreign material and is internally sprayed with a coating of adhesive. This adhesive is allowed to dry or cure; thereby creating a film on the internal surface of the pipe. This adhesive is allowed to flow into the J-section (per API Spec 5B) of the coupling and around the tapered segment of the pin end.

The PVC liner to be installed into the steel tubular is coated with a layer of adhesive that is compatible with the adhesive which was sprayed into the steel tubular. This adhesive is allowed to dry or cure. The liner to be installed in threaded and coupled pipe requires a seal ring to be chemically bonded to the PVC liner. The cured seal ring will function as a seat in the J-section of the threaded and coupled pipe.

When both adhesives are cured the liner is inserted into the steel tubular to proceed through the bonding and finishing process.

Special tools are placed on the ends of the pipe and used to pack off the liner. A combination of heat and pressure is applied to the steel and liner assembly so as to expand the liner to conform to the ID of the steel tubing and to reactivate the adhesives. The unit is cooled, allowing the reset of the adhesives. The PVC liner is now in position against the wall of the steel.

The coupling and pin ends of the lined tubular are hand dressed to create the seating surfaces of the PVC liner at a pre-determined depth. A mark is placed on the pin end to designate the desired depth of make-up to seat the PVC liner in the J-section of the lined steel tubular.

The lined pipe, coupling and pin areas are checked and dope is applied to the connection. Pin end protectors are placed on the pipe.

**b. FABRICATION PROCESS "B"**

**INSTALLATION OF THE LINER** — The entire inside diameter of each tubular is sandblasted to remove any remaining scale or other foreign matter. The extruded PVC liner is then sleeved inside the steel joint. The liner is pulled past the coupling, inserted into a special device for heating the PVC liner and a precision designed mandrel is exposed to the heated liner end and causes the end to flare slightly. The liner is drawn back into the coupling flush with the end of the tubular.

A special machined connection is threaded onto the pin-end of the joint and the coupling end is elevated and aligned with a splash plate. A hose is inserted into the special pin-end connection and a portland cement slurry is pumped, at controlled pressures, between the outside diameter of the liner and the inside diameter of the steel tubular. Elevating the pipe while injecting the cement slurry assures that it is uniformly applied to minimize voids between the PVC liner and the steel goods. The cement slurry is then allowed to cure for a specified length of time.

A machined spacer is used to gauge the amount of PVC liner protruding past the exposed pin-end of the tubular. The liner is inserted into a specially designed heating device and flared with a precision mandrel around the pin-end of the pipe.

The threads of the coupling and the pin-end (having already been cleaned) are dressed with a special light protective compound. A small amount of teflon based pipe dope is applied to the threads of the coupling only. A plastic thread protector is threaded onto the pin-end and the pipe receives a layer of corrosion resistant aluminum tank coating on the full outside diameter of the pipe. Finally, there is a special identification number (lot number) assigned to the tubular and permanently applied to the steel tubular surface.

**c. FABRICATION PROCESS "C"**

1. The interior surface of the steel line pipe or tubing is cleaned by abrasive blasting.
2. The lining is formed by inserting a rigid PVC liner with a modified exterior surface texture, into the conditioned steel tubular. The annular space between the PVC liner and steel tubular is filled with a portland cement mortar.
3. After the liner is placed, mortar is pumped at a controlled rate through a lining cap on one end of the tubular into the annulus between the steel tubular and PVC liner. After returns at the opposite end of the tubular are evident, the pressure is raised to just below the collapse pressure of the tube to effect a squeeze and cause partial dehydration of the mortar.
4. The mortar is locked in the annular space under pressure and the mortar is allowed to set before removing the cap.
5. The end cap is removed and the ends of the liner are flared over the ends of the steel tubular. If the tubular being lined is threaded and coupled, the flare on the coupling end is prepared and placed in proper position before the annulus is filled with mortar.
6. A reference band is stenciled on the pin end.
7. The lined tubular is thoroughly cleaned and inspected. Threads are brushed clean and a protective coating applied. Once the tubular has passed visual inspection, thread protectors are placed on the pin end and plugs inserted in the coupling.

**3.4 REPAIRS.** Defects in new lined systems are typically not repaired — the manufacturer will replace any defective liners found during the manufacturing process. Repair kits are available for field end repair. Note that these repairs result in a liner system which is no longer one continuous piece.

Repair methods may be field applied, shop repaired, or re-lined depending on the type of damage. Distinct differences in the lined products require contacting the appropriate lining manufacturer to determine the repair requirements for damaged PVC lined steel tubular goods.

## SECTION 4

### MATERIAL COMPOSITION

**4.1 CHEMICAL.** The poly (vinyl chloride) (PVC) extrusion compound shall meet the requirements for PVC class 12454B; or class 12454C; as set forth in ASTM D 1784.

**4.2 POLYMER CONTENT.** The homopolymer portion of the PVC compound shall contain a minimum of 88% vinyl chloride.

**4.3 ASH COMPOSITION.** The ash composition shall contain  $65\% \pm 3\%$  by weight of calcium carbonate and  $35\% \pm 3\%$  by weight of titanium dioxide.

**4.4 SPECIFIC GRAVITY.** The PVC liner extrusion compound shall have a specific gravity range of 1.32-1.47, as determined by ASTM D 792 method A.3 (testing of compound prior to extrusion process).

**4.5 CERTIFICATION.** Manufacturers shall retain records of certification for all requirements of Section 4. A change of compounder or compound formulation shall require recertification documentation.

## SECTION 5

### PHYSICAL PROPERTIES, TESTS, AND REQUIREMENTS

#### 5.1 EXTRUDED PRODUCT TESTING AND REQUIREMENTS

(Testing of PVC at extruder location.)

**a. TEST CONDITIONS.** Tests shall be conducted in laboratory atmosphere of  $73.4 \pm 3.6^\circ\text{F}$  and  $50 \pm 5$  percent relative humidity, unless otherwise specified in the test methods or in this specification. In cases of disagreement, the tolerances shall be  $\pm 1.8^\circ\text{F}$  and  $\pm 2$  percent relative humidity.

**b. IMPACT RESISTANCE OF PVC LINER.** The method of test shall be ASTM D 2444 with a Tup B and a flat plate support. Use a 20 lb. tup for liners 12 in. and smaller. Impact tests shall exceed the minimum values listed in Table 5.1; herein.

**c. EXTRUSION QUALITY (ACETONE TEST).** PVC liners shall meet the requirements of ASTM D 2152. Anhydrous acetone shall be used and the liner exposed not less than 20 minutes.

**d. FLATTENING.** Three specimens of the liner shall be flattened. The specimens shall be 2 inches long and placed between parallel plates in a suitable press until the distance between the plates is 40 percent of the outside diameter of the liner or the walls of the liner touch. The rate of loading shall be uniform and such that the compression is completed within 2 to 5 minutes. On removal of the load, the specimens shall be examined for evidence of splitting, cracking, or breaking.

**e. FREQUENCY OF TESTS.** Specific gravity test as specified in 4.4 shall be conducted on a manufacturers batch or lot basis. Impact tests shall be tested at 4-hour intervals for each extrusion line as specified in Par. 5.1.b. Extrusion quality (acetone test) shall be performed at 8-hour intervals for each extrusion line as specified in Par. 5.1.c. Dimensions and tolerances of each piece of liner shall be checked with rejection of any piece exceeding tolerances specified by manufacturer. Flattening tests as specified in Par. 5.1.d shall be run at 8-hour intervals. Quality control records shall contain data of all tests and be open to inspection by the manufacturer.

**f. REWORK MATERIAL.** Regrind materials shall not be permitted as part of the PVC liner products.

**g. RETEST AND REJECTION.** When the liner fails to meet the specifications requirements in any test, additional testing shall be made on previously produced liners until 3 separate, sequential, acceptable results are obtained. Liners that do not meet the requirement shall be rejected, and recorded.

**TABLE 5.1**  
**IMPACT RESISTANCE @  $73.4^\circ\text{F}$ \***  
**FOR PVC LINERS AS EXTRUDED**

1	2
Size OD-Inches	IMPACT RESISTANCE Ft-lbs, All SDR's
1.32 - 1.89	20
1.90 - 2.38	30
2.39 - 2.87	40
2.88 - 3.49	60
3.50 - 4.00	70

\*Test Method ASTM D 2444 as specified in Par. 5.1.b

#### 5.2 FABRICATED PRODUCT REQUIREMENTS

**a. WORKMANSHIP.** The liner shall be homogeneous throughout and free from visible cracks, holes, protrusions, foreign inclusions, or other injurious defects, as established by the manufacturer. The liner shall be uniform within the manufacturers acceptable limits in terms of color, out-of-roundness, density and physical properties.

**b. LENGTHS.** All liners shall be one continuous extruded piece capable of fully sleeving the entire length of the steel tubular in which it is to be installed. In this context continuous means "one solid piece not requiring splicing to another liner." Therefore, the liner lengths are strictly dependent on the range/length of the steel tubular being lined.

**c. NOMINAL INSIDE DIAMETER.** The nominal inside diameter of the PVC lined steel pipe or tubing, as shown in Tables 5.2 and 5.3, column 4.

**d. WALL THICKNESS.** A dimension of the minimum wall thickness at any cross section of the PVC liner prior to the fabrication process, shall be as shown in Tables 5.2 and 5.3, column 5.

**e. WEIGHT OF LINING MATERIALS.** The nominal weight of the lining materials added to the steel pipe or tubing expressed as pounds per foot, as shown in Tables 5.2 and 5.3, column 6.

**f. DRIFT DIAMETER.** A specified dimension for which a cylindrical or spherical mandrel shall pass freely through the entire length of the finished PVC lined steel line pipe or tubing, at the manufacturers facility. Cylindrical mandrels shall have a minimum length not less than the drift diameter, as shown in Tables 5.2 and 5.3, column 7.

**NOTE:** Manufacturers written specifications for weights and dimensions should be used as reference for engineering design. Inside diameters and lining weights may vary due to the process of manufacture.

**TABLE 5.2**  
**PVC LINED LINE PIPE**  
**DIMENSIONS & WEIGHTS**  
 See Appendix E For Metric Conversion

1	2	3	4	5	6	7
NOMINAL PIPE SIZE (inches)	PIPE SCHEDULE	MFG PROCESS (Refer Sec 3)	NOMINAL INSIDE DIA. (inches)	WALL THICKNESS (inches)	WEIGHT OF LINER SYSTEM (Lbs/Ft)	MINIMUM DRIFT DIA. (inches)
2	40	A	1.900	.065	.260	1.840
3	40	A	2.900	.070	.435	2.800
4	40	A	3.850	.075	.623	3.750
2	40	B	1.770	.065	.44	1.67
2	80	B	1.770	.065	.44	1.67
2 1/2	40	B	2.160	.070	.65	2.06
2 1/2	80	B	2.160	.070	.65	2.06
3	40	B	2.735	.070	.75	2.635
3	80	B	2.735	.070	.75	2.635
2	40	C	1.780	.060	.50	1.700
2 1/2	40	C	2.195	.073	.55	2.110

**TABLE 5.3**  
**PVC LINED TUBING**  
**DIMENSIONS & WEIGHTS**  
 See Appendix E For Metric Conversion

1 SIZE (inches)	2 NOMINAL WEIGHTS		3 MFG PROCESS (Refer Sec. 3)	4 NOMINAL INSIDE DIAMETER (inches)	5 WALL THICKNESS (Lbs/Ft)	6 WEIGHT LINER SYSTEM (Lbs/Ft)	7 MINIMUM DRIFT DIA. (inches)
	NON-UPSET T & C	UPSET T & C					
1.660	2.30	2.40	A	1.240	.060	.153	1.15
1.900	2.75	2.90	A	1.475	.060	.190	1.360
2 3/8	4.60	4.70	A	1.860	.065	.260	1.750
2 7/8	6.40	6.50	A	2.300	.065	.320	2.200
3 1/2	9.20	9.30	A	2.830	.070	.435	2.70
1.315	1.70	1.80	B	.840	.050	.20	.740
1.900	2.75	2.90	B	1.425	.060	.22	1.325
2.063	3.25	NA	B	1.425	.060	.53	1.325
2 3/8	4.60	4.70	B	1.770	.065	.44	1.670
2 7/8	6.40	6.50	B	2.160	.070	.65	2.060
3 1/2	9.20	9.30	B	2.735	.070	.75	2.635
4 1/2	12.60	12.75	B	3.635	.090	1.19	3.535
1.660	2.30	2.40	C	1.189	.063	.25	1.115
2 3/8	4.60	4.70	C	1.780	.060	.50	1.700
2 7/8	6.40	6.50	C	2.195	.073	.55	2.110

## SECTION 6 END PROTECTION

**6.1 THREADED ENDS.** Thread condition is important to the sealing effectiveness of the PVC lining system, but gauging the thread elements (lead, taper, height, stand-off) is beyond the scope of this document. Couplings shall be screwed onto the pipe power-tight. A thread compound shall be applied to cover the full surface of either the coupling or pipe engaged thread before making up the joint. All exposed threads shall be coated with a thread compound or a storage compound of distinct color. Unless otherwise specified on the purchase order, the manufacturer may use any thread compound which meets the performance objectives set forth in API Bulletin 5A2. Whichever compound is used shall be applied to a surface that is clean, free of moisture and cutting fluids, as established by Manufacturers procedures.

**6.2 END PROTECTION.** The manufacturer shall provide pin end thread protection of such design, material, and mechanical strength to protect the pin ends of the lined tubular from damage under normal handling and transportation and to prevent damage by ultra-violet radiation and other weather elements. Threaded box ends do not require protection, unless specified in writing by purchaser. Non-threaded connections may have special end protection requirements and are subject to written agreement between purchaser and manufacturer.

*NOTE: End closures are effective in keeping debris out of the ID, however, with both ends closed there is some concern with excessive heat buildup in hot climates. Therefore, this standard only requires protection to pin ends.*

## SECTION 7 COUPLINGS

Each manufacturer shall be responsible for the corrosion barrier integrity of the coupling placed in the PVC liner system. Any connection covered under API Specification 5CT may be used by each fabrication process.

Proprietary connections may also be used on products covered by this specification but such connections are beyond the scope of this specification.

## SECTION 8 INSPECTION

**8.1 PURCHASER INSPECTION.** Unless otherwise provided, the provisions of Appendix E shall apply.

**8.2 INSPECTION SUMMARY.** Table 8.1 below summarizes the inspection and documentation required for both new and used products. Refer to the relevant paragraph for detailed requirements.

Table 8.1  
INSPECTION SUMMARY

INSPECTION CATEGORY	INSPECTION ATTRIBUTE	SUMMARY OF CRITERIA	RELEVANT PARAGRAPH
STEEL SURFACE PREP.	ABRASIVE BLAST	The interior shall be essentially free of mill varnish, oil, paraffin, corrosion products, scale, loose mill scale, thread lubricant and any other foreign material. 'Essentially free' means a minimum of NACE #4 Brush-Off Blast surface finish. Tightly adhering coatings are acceptable after blasting.	Note 1
PVC LINER COMPOSITION	MATERIAL CLASS	Document that PVC is ASTM D 1784 Class 12454B or 12454C	4.1, 4.5
	POLYMER CONTENT	Document that homopolymer portion of PVC compound contains at least 88% vinyl chloride.	4.2, 4.5
	ASH COMPOSITION	Document that ash contains $65 \pm 3$ WT. % $\text{CaCO}_3$ and $35 \pm 3$ WT. % $\text{TiO}_2$	4.3, 4.5
PVC LINER REQUIREMENTS	SPECIFIC GRAVITY	Document that ASTM D 792 (Method A.3) specific gravity is within range of 1.32-1.47	4.4, 4.5
	IMPACT	Document ASTM D 2444 (TUP B, 20 lb for liners $\leq 12$ in.) Impact results are per Table 5.1	5.1.b, 5.1.g

Note 1: See National Association of Corrosion Engineers (NACE) Standard TM0170-70 for Brush-Off Blast NACE #4.

INSPECTION CATEGORY	INSPECTION ATTRIBUTE	SUMMARY OF CRITERIA	RELEVANT PARAGRAPH
FINAL LINED PRODUCT	ACETONE TEST	Document ASTM D2152 tests using anhydrous acetone for not less than 20 minutes	5.1.c, 5.1.g
	FLATTENING	Document flattening tests	5.1.d, 5.1.g
	REWORK MATERIAL	No regrind material allowed.	5.1.f
	PVC LINER	Visually verify that liner is one continuous piece, free from cracks, holes, protrusions, inclusions, or other injurious defects as established by the manufacturer. The liner shall be uniform in terms of color and out of roundness.	5.2.a, 5.2.b
	DIMENSIONS	Document dimensions are per Tables 5.2 and 5.3	5.2.c, 5.2.d
	DRIFT	Verify minimum drifts per Tables 5.2 & 5.3	5.2.f
	THREADS	Verify that: <ul style="list-style-type: none"> <li>Couplings are applied power tight</li> <li>Thread/storage compounds are applied</li> <li>Pin end protectors installed</li> <li>Box end protectors installed if specified (2)</li> </ul>	6.1 6.1 6.2 6.2
		(Note: This specification does not require inspection of the threads themselves)	(6.1)
	MARKING	Verify each joint marked with water resistant paint or ink stencil. <ul style="list-style-type: none"> <li>As above with die stamping if specified (2)</li> </ul>	9.1, 9.2 9.1, 9.2

NOTES: (2) This item is subject to agreement between manufacturer and purchaser.



## SECTION 9 EQUIPMENT MARKING

**9.1 METHODS AND REQUIREMENTS.** PVC lined tubulars which have been lined in conformance with this specification shall be marked by the manufacturer as specified in Par 9.2. (Additional marking as desired by the Manufacturer or as requested by the Purchaser are not prohibited). Markings shall be readily visible as applied by water resistant paint or ink stencil. Die stamping may be substituted for any marking requirements as agreed upon between purchaser and manufacturer. Markings shall not overlap and shall be applied in such a manner as not to injure the pipe or couplings. Markings shall be applied within three feet of the connection.

*NOTE: Die stamping is prohibited by API Spec 5CT Group 2 products.*

### 9.2 SEQUENCE:

a. Specification and process designation, see Section 3, Ex.: 15LT-A for process A.

When applicable,\* the API license number shall be applied in lieu of 15 LT.

b. Date of Manufacture; month and year, Ex.: Jan. 93 = 1/93.

c. Unique manufacturers lot identification number.

Example: Tubulars lined by process A on January 1993 should be marked as follows:

15LT-A-1/93-(ID#)

\*Users of this specification should note that there is no longer a requirement for marking a product with the API monogram. The American Petroleum Institute continues to license use of the monogram on products covered by this specification but it is administered by the staff of the Institute separately from the specification. The policy describing use of the monogram is contained in Appendix B herein. No other use of the monogram is permitted. Non-Licensees may mark products in conformance with Section 9 and Licensees may mark products in conformance with Appendix B.

## SECTION 10 RECORD RETENTION REQUIREMENTS

**10.1 PURPOSE.** The quality control records required by this specification are necessary to substantiate that all materials and products made to meet this specification do conform to the specified requirements.

### 10.2 RECORDS CONTROL.

a. Quality control records required by this specification shall be legible, identifiable, retrievable and protected from damage, deterioration, or loss.

b. Quality control records required by this specification shall be retained by the Manufacturer for a minimum of five years following the date of manufacture.

c. All quality control records required by this specification shall be signed and dated, as established by the Manufacturer's procedures.

### 10.3 OTHER RECORDS TO BE MAINTAINED BY MANUFACTURER.

Any records related to Manufacturer's process documentation, as defined in the manufacturer's procedures, shall be maintained by manufacturer as noted in Par. 10.2.

# **APPENDIX A** **RECOMMENDED CHEMICAL RESISTANCE TABLE** (These test values are valid at 0 PSIG pressure only)

E = Excellent	U = Unsuitable
G = Good	O = No test
L = Limited	

Chemical	72°F.	140°F.	Chemical	72°F.	140°F.
Acetaldehyde	U	U	Benzaldehyde	U	U
Acetamide	O	O	Benzene	U	U
Acetate Solvents — Crude	U	U	Benzenesulfonic Acid — 10%	E	E
Acetate Solvents — Pure	U	U	Benzenesulfonic Acid	U	U
Acetic Acid 0-10%	E	E	Benzoic Acid	E	E
Acetic Acid 10-20%	E	E	Benzol	U	U
Acetic Acid 20-30%	E	G	Bismouth Carbonate	E	E
Acetic Acid 30-60%	E	E	Black Liquor (Paper Industry)	E	E
Acetic Acid 80%	G	L	Bleach — 12.5% Active Cl <sub>2</sub>	E	G
Acetic Acid — Glacial	G	U	Borax	E	E
Acetic Acid — Vapors	E	E	Borax Liquors	E	E
Acetic Anhydride	U	U	Boric Acid	E	E
Acetone	U	U	Boron, Trifluoride	E	E
Acetylene	L	L	Breeder Pellets — Fish Derivative	E	E
Adipic Acid	E	E	Brine	E	E
Alcohol — Allyl — 96%	G	L	Bromic Acid	E	E
Alcohol — Amyl	E	L	Bromine — Liquid	U	U
Alcohol — Butyl	E	G	Bromine (Gas) — 25%	E	E
Alcohol — Ethyl	E	E	Bromine — Water	E	E
Alcohol — Methyl	E	E	Butadiene	E	E
Alcohol — Propargyl	E	E	Butane	E	E
Alcohol — Propyl	E	E	Butane, Butylene	E	E
Allyl — Chloride	U	U	Butane, Diol	E	E
Alum	E	E	Butanol	E	U
Alum, Ammonium	E	E	Butanol — Primary	E	E
Alum, Chrome	E	E	Butanol — Secondary	E	L
Alum, Potassium	E	E	Buttermilk	E	E
Aluminum Chloride	E	E	Butyl Acetate	U	U
Aluminum Fluoride	E	E	Butyl Phenol	E	U
Aluminum Hydroxide	E	E	Butylene	E	O
Aluminum Oxychloride	E	E	Butynediol (Erythritol)	E	U
Aluminum Nitrate	E	E	Butyric Acid 20%	G	U
Aluminum Sulfate	E	E	Butyric Acid	E	U
Ammonia — Dry Gas	E	E			
Ammonia, Aqua (10%)	E	E	Calcium Bisulfide	E	E
Ammonia — Liquid	L	U	Calcium Bisulfite	E	E
Ammonium Acetate	E	E	Calcium Carbonate	E	E
Ammonium Bifluoride	E	E	Calcium Chlorate	E	E
Ammonium Carbonate	E	E	Calcium Chloride	E	E
Ammonium Chloride	E	E	Calcium Hydroxide	E	E
Ammonium Fluoride — 25%	E	L	Calcium Hypochlorite	E	E
Ammonium Hydroxide — 28%	E	E	Calcium Nitrate	E	E
Ammonium Metaphosphate	E	E	Calcium Oxide	E	E
Ammonium Monophosphate	E	E	Calcium Sulfate	E	E
Ammonium Nitrate	E	E	Cane Sugar Liquors	E	E
Ammonium Persulfate	E	E	Carbolic Acid	E	E
Ammonium Phosphate (Ammoniacal)	E	E	Carbon Bisulfide	U	U
Ammonium Phosphate — Neutral	E	E	Carbon Dioxide (Aqueous S.L.)	E	E
Ammonium Sulfate	E	E	Carbon Dioxide Gas (Wet)	E	E
Ammonium Sulfide	E	E	Carbon Monoxide	E	E
Ammonium Thiocyanate	E	E	Carbon Tetrachloride	L	U
Amyl Acetate	U	U	Carbonated Water	E	E
Amyl Chloride	U	U	Carbonic Acid	E	E
Aniline	U	U	Caseln	E	E
Aniline Chlorohydrate	U	U	Castor Oil	E	E
Aniline Dyes	U	U	Caustic Potash	E	E
Aniline Hydrochloride	U	U	Caustic Soda	E	E
Anthraquinone	E	E	Cellosolve	G	L
Anthraquinonesulfonic Acid	E	E	Chloracetic Acid	E	L
Antimony Trichloride	E	E	Chloral Hydrate	E	E
Aqua Regia	E	L	Chloric Acid 20%	E	E
Arsenic Acid — 80%	E	G	Chlorinated Solvents	U	U
Arylsulfonic Acid	E	E	Chlorine (Dry)	E	L
Asphalt	E	E	Chlorine Gas (Moist)	G	E
			Chlorine Water	E	E
Barium Carbonate	E	E	Chloroacetic Acid	E	E
Barium Chloride	E	E	Chlorobenzene	U	U
Barium Hydroxide	E	E	Chlorobenzyl Chloride	U	U
Barium Sulfate	E	E	Chloro Form	U	U
Barium Sulfide	E	E	Chlorosulfonic Acid (100%)	E	U
Bear	E	E	Chrome Alum	E	E
Beet — Sugar Liquor	E	E	Chromic Acid 10%	E	E

Chemical	72°F.	140°F.	Chemical	72°F.	140°F.
Chromic Acid 25%	E	L	Gas — Natural (Dry)	E	E
Chromic Acid 30%	E	L	Gas — Natural (Wet)	E	E
Chromic Acid 40%	E	L	Gasoline (Leaded)	E	E
Chromic Acid 50%	E	L	Gasoline (Unleaded)	E	E
Citric Acid	E	E	Gasoline — Refined	E	E
Coconut Oil	E	E	Gasoline — Sour	E	E
Coke Oven Gas	E	E	Gelatine	E	E
Copper Carbonate	E	E	Glucose	E	E
Copper Chloride	E	E	Glycerine (Glycerol)	E	E
Copper Cyanide	E	E	Glycol	E	E
Copper Fluoride	E	E	Glue	E	E
Copper Nitrate	E	E	Glycolic Acid 30%	E	E
Copper Sulfate	E	E	Green Liquor (Paper Industry)	E	E
Core Oils	E	E			
Corn Oil	E	E	Heptane	E	G
Corn Syrup	E	E	Hexane	E	L
Cottonseed Oil	E	E	Hexanol Tertiary	E	E
Cresol	U	U	Hydrobromic Acid — 20%	E	E
Cresylic Acid 50%	E	E	Hydrochloric Acid — 0-25%	E	E
Croton Aldehyde	U	U	Hydrochloric Acid — 25-40%	E	E
Crude Oil — Sour	E	E	Hydrocyanic Acid or Hydrogen Cyanide	E	E
Crude Oil — Sweet	E	E	Hydrofluoric Acid 4%	E	L
Cuprous Chloride	E	E	Hydrofluoric Acid 10%	E	E
Cyclohexane	U	U	Hydrofluoric Acid 48%	E	L
Cyclohexanol	U	U	Hydrofluoric Acid 60%	E	L
Cyclohexanon	U	U	Hydrofluoric Acid 100%	G	L
			Hydrogen	E	E
Deminerlized Water	E	E	Hydrogen Peroxide — 30%	E	E
Dextrin	E	E	Hydrogen Peroxide — 50%	E	E
Dextrose	E	E	Hydrogen Peroxide — 90%	E	E
Diazo Salts	E	E	Hydrogen Sulfide — Aqueous Solution	E	E
Diesel Fuels	E	E	Hydrogen Sulfide — Dry	E	E
Diethy Amine	U	U	Hydroquinone	E	E
Diethylphthalate	U	U	Hydroxylamine Sulfate	E	E
Disodium Phosphate	E	U	Hypochlorous Acid	E	E
Diethyl Ether	U	G	Hypo-(Sodium Thiosulfate)	E	E
Diglycolic Acid	E	G			
Dioxane — 1, 4	O	O	Iodine	U	U
Divinyl Benzene	O	O	Iodine (in Alcohol)	U	U
Drying Oil	O	O	Iodine Solution (10%)	U	U
			Iodoform	O	O
Elhers	U	U	Isopropylalcohol	E	E
Ethyl Acetate	U	U			
Ethyl Acrylate	U	U	Jet Fuels, JP4 & JP5	E	E
Ethyl Chloride	U	U			
Ethyl Ether	U	U	Kerosene	E	E
Ethylene Bromide	U	U	Ketones	U	E
Ethylene Chlorohydrin	U	U	Kraft Liquor (Paper Industry)	E	E
Ethylene Dichloride	U	U			
Ethylene Glycol	E	E	Lacquer Thinners	L	U
Ethylene Oxide	U	U	Lactic Acid 28%	E	E
			Lard Oil	E	E
Fatty Acids	E	E	Lauric Acid	E	E
Ferric Chloride	E	E	Lauryl Chloride	E	E
Ferric Nitrate	E	E	Lauryl Sulfate	E	E
Ferric Sulfate	E	E	Lead Acetate	E	E
Ferrous Nitrate	E	E	Lime Sulfur	E	E
Fish Solubles	E	E	Linoleic Acid	E	E
Fluorine Gas — Dry	L	U	Linseed Oil	E	E
Fluorine Gas — Wet	L	U	Liquors	E	E
Fluoroboric Acid — 25%	E	E	Liquors	E	E
Fluorosilicic Acid	E	E	Lithium Bromide	E	E
Formaldehyde	E	G	Lubricating Oil	E	E
Food Products such as Milk, Buttermilk, Molasses, Salad Oils, Fruit	E	E			
Formic Acid	E	U	Machine Oil	E	E
Freon — 12	E	G	Magnesium Carbonate	E	E
Fructose	E	E	Magnesium Chloride	E	E
Fruit Pulps and Juices	E	E	Magnesium Citrate	E	E
Fuel Oil (containing H <sub>2</sub> SO <sub>4</sub> )	E	E	Magnesium Hydroxide	E	E
Furfural	U	U	Magnesium Nitrate	E	E
			Magnesium Sulfate	E	E
Gallic Acid	E	E	Maleic Acid	E	E
Gas — Coke Oven	E	E	Malic Acid	E	E
Gas — Manufactured	U	U	Mercuric Chloride	E	E
			Mercuric Cyanide	E	E

## Spec 15LT: PVC Lined Steel Tubular Goods

19

Chemical	72°F.	140°F.	Chemical	72°F.	140°F.
Mercurous Nitrate	E	E	Phosphorous (Red)	E	E
Mercury	E	E	Phosphorous Pentoxide	E	E
Methane	E	E	Phosphorous Trichloride	E	L
Methyl Bromide	U	U	Photographic Chemicals	E	U
Methyl Cellosolve	U	U	Photographic Solutions	E	E
Methyl Chloride	U	U	Phthalic Acid	O	O
Methyl Chloroform	U	U	Picric Acid	U	U
Methyl Ethyl Ketone	U	U	Plating Solutions:		
Methyl Iso-Butyl Ketone	U	U	Brass	E	E
Methyl Salicylate	E	E	Cadmium	E	E
Methyl Sulfate	E	L	Chromium	E	G
Methyl Sulfonic Acid	E	E	Copper	E	E
Methyl Sulfuric Acid	E	E	Gold	E	E
Methylene Chloride	U	U	Iron	E	E
Milk	E	E	Judium	E	E
Mineral Oils	E	E	Lead	E	E
*Mixed Acids (H <sub>2</sub> SO <sub>4</sub> & HNO <sub>3</sub> )	E	E	Nickel	E	E
Molasses	E	E	Rhodium	E	E
Monoethanolamine	U	U	Silver	E	E
Muriatic Acid	E	E	Tin	E	E
			Zinc	E	E
Naptha	E	E	Potassium Acid Sulfate	E	E
Napthalene	U	U	Potassium Aluminum Sulfate	E	E
Natural Gas, Dry & Wet	E	E	Potassium Alum	E	E
Nickel Acetate	E	E	Potassium Antimonate	E	E
Nickel Chloride	E	E	Potassium Bicarbonate	E	E
Nickel Nitrate	E	E	Potassium Bichromate	E	E
Nickel Sulfate	E	E	Potassium Bisulfite	E	E
Nickel Sulphate	E	E	Potassium Borate 1%	E	E
Nicotine	E	E	Potassium Borate	E	E
Nicotine Acid	E	E	Potassium Bromate 10%	E	E
Nitric Acid Anhydrous	U	U	Potassium Bromate	E	E
Nitric Acid 10%	E	E	Potassium Bromide	E	E
Nitric Acid 20%	E	L	Potassium Carbonate	E	E
Nitric Acid 35%	E	G	Potassium Chlorate (ag)	E	E
Nitric Acid 40%	E	G	Potassium Chlorate	E	E
Nitric Acid 60%	E	L	Potassium Chloride	E	E
Nitric Acid 68%	G	U	Potassium Chromate (Aln)	E	E
Nitric Acid 70%	E	U	Potassium Chromate (Neut.)	E	E
Nitric Acid 100%	E	U	Potassium Chromate 40%	E	E
Nitric Acid, Red Fuming	U	U	Potassium Cuprocyanide	E	E
Nitrobenzene	U	U	Potassium Cyanide	E	E
Nitropropane	O	O	Potassium Dichromate 40%	E	E
Nitrous Acid (10%)	E	E	Potassium Dichromate	E	E
Nitrous Oxide	E	E	Potassium Dichrom (Alkaline)	E	E
			Potassium Dichrom (Neutral)	E	E
Oenol (Unsaturated Alcohol)	E	E	Potassium Diphosphate	E	E
Oil and Fats	E	E	Potassium Ferricyanide	E	E
Oleic Acid	E	E	Potassium Ferrocyanide	E	E
Oleum	U	U	Potassium Fluoride	E	E
Oxalic Acid	E	E	Potassium Hydroxide	E	E
Oxygen	E	E	Potassium Hypochlorite	E	G
Ozone	Q	L	Potassium Iodide	E	E
			Potassium Nitrate	E	E
Palmitic Acid 10%	E	E	Potassium Perborate	E	E
Palmitic Acid 70%	E	U	Potassium Perchlorate	E	E
Paraffin	E	E	Potassium Perchlorite	E	E
Pentane	O	O	Potassium Permanganate 10%	E	E
Peracetic Acid 40%	E	U	Potassium Permanganate 25%	G	L
Perchloric Acid 10%	E	L	Potassium Persulfate	E	E
Perchloric Acid 15%	E	U	Potassium Sulfate	E	E
Perchloric Acid 70%	E	U	Potassium Sulfide	E	E
Perchloroethylene	O	O	Potassium Thiosulfate	E	E
Petrolatum	E	E	Propane	E	E
Phenol	L	U	Propylene Dichloride	U	U
Phenol (90%)	U	U	Propylene Glycol	E	E
Phenylhydrazine	U	U	Pyrogalllic Acid	O	O
Phenylhydrazine — Hydrochloride	E	U			
Phosgene (Gas)	E	U	Rayon Coagulating Bath	E	E
Phosgene (Liquid)	U	U	Rochelle Salts	E	E
Phosphoric Acid 0-25%	E	G			
Phosphoric Acid 25-50%	E	E	Sea Water	E	E
Phosphoric Acid 50-75%	E	E	Salen's Acid (Aqueous)	O	O
Phosphoric Acid — 85%	E	E	Salicylaldehyde	O	O
Phosphorous (Yellow)	E	G	Salt Water	E	E

Chemical	72°F.	140°F.	Chemical	72°F.	140°F.
Selenic Acid	E	E	Sulphuric Acid 0-10%	E	E
Sewage	E	E	Sulphuric Acid 10-30%	E	E
Silicic Acid	E	E	Sulphuric Acid 30-50%	E	E
Silver Cyanide	E	E	Sulphuric Acid 50-75%	E	E
Silver Nitrate	E	E	Sulphuric Acid 75-90%	E	E
Silver Sulfate	E	E	Sulphuric Acid 95%	E	Q
Soap Solution	E	E	Sulphurous Acid	G	U
Soaps	E	E			
Sodium Acetate	E	E	Tan Oil	E	E
Sodium Alum	E	E	Tannic Acid	E	E
Sodium Acid Sulfate	E	E	Tanning Liquors	E	E
Sodium Aluminate	E	E	Tartaric Acid	E	E
Sodium Antimonate	E	E	Tetrachloroethane	O	O
Sodium Arsenite	E	E	Tetraethyl Lead	E	Q
Sodium Benzoate	E	E	Tetrahydro Furane	U	U
Sodium Bicarbonate	E	E	Thionyl Chloride	U	U
Sodium Bisulfate	E	E	Tepineol	G	L
Sodium Bisulfite	E	E	Tin Chloride	E	E
Sodium Borate	E	E	Titanium Tetrachloride	U	U
Sodium Bromide	E	E	Toluol or Toluene	U	U
Sodium Carbonate (Soda Ash)	E	E	Toxaphene (90%)	O	O
Sodium Chlorate	E	G	Tributyl Phosphate	U	U
Sodium Chloride	E	E	Trichloroacetic Acid	E	E
Sodium Chlorite	E	E	Trichloroethylene	U	U
Sodium Cyanide	E	E	Tricresylphosphate	U	U
Sodium Dichromate	E	E	Triethanolamine	E	G
Sodium Dichromate (Neutral)	E	E	Triethylamine	E	G
Sodium Ferricyanide	E	E	Trimethyl Propane	E	E
Sodium Ferrocyanide	E	E	Trisodium Phosphate	E	E
Sodium Fluoride	E	E	Turpentine	E	E
Sodium Hydroxide 10%	E	E			
Sodium Hydroxide 15%	E	E	Urea	E	E
Sodium Hydroxide 35%	E	E	Urine	E	E
Sodium Hydroxide 70%	E	E			
Sodium Hydroxide (Satr)	E	E	Vegetable Oil	E	E
Sodium Hypochlorite	E	E	Vinegar	E	E
Sodium Iodide	E	E	Vinyl Acetate	U	U
Sodium Nitrate	E	E			
Sodium Nitrite	E	E	Water — Acid Mine	E	E
Sodium Perborate	E	E	Water — Distilled	E	E
Sodium Peroxide	E	E	Water — Fresh	E	E
Sodium Phosphate	E	E	Water — Salt	E	E
*Sodium Phosphate — Acid	E	E	Water — Sewage	E	E
Sodium Silicate	E	E	Whiskey	E	E
Sodium Sulfate	E	E	White Gasoline	E	E
Sodium Sulfide	E	E	White Liquor (Paper Industry)	E	E
Sodium Sulfite	E	E	Wines	E	E
Sodium Thiosulfate (Hypo)	E	E			
Sour Crude Oil	E	E	Xylene or Xylol	U	U
Stannic Chloride	E	E			
Stannous Chloride (50%)	E	E	Zinc Chloride	E	E
Stannous Chloride	E	G	Zinc Chromate	E	E
Starch	E	E	Zinc Cyanide	E	E
Stearic Acid	E	E	Zinc Nitrate	E	E
Stoddards Solvent	E	E	Zinc Sulfate	E	E
Sulfated Detergents	E	E			
Sulfur	E	E	Mixtures of Acids:		
Sulfur Dioxide Gas — Dry	E	E	Nitric 15% — Hydrofluoric 4%	E	E
*Sulfur Dioxide Gas — Wet	E	E	Sodium Dichromate 13% — Nitric	E	E
Sulfur Trioxide	E	L	Acid 16%/Water 71%		
Sulphur Dioxide — Liquid	G	U			

This information may be used as a guide to assist in the proper application of PVC lined tubulars. It is suggested tests be run for critical applications.

## APPENDIX B MARKING INSTRUCTIONS FOR API LICENSEES

**a. GENERAL.** Products manufactured in conformance with this specification may be API monogrammed by the API licensed manufacturer, such Products which are monogrammed shall be marked as specified hereinafter. (Additional markings as desired by the manufacturer or as requested by the Purchaser are not prohibited.) Markings shall be readily visible as applied by water resistant paint or ink stencil. Die stamping may be substituted for any marking requirements as agreed upon between purchaser and manufacturer. Markings shall not overlap and shall be applied in such a manner as not to injure the pipe or couplings. Markings shall be applied within three feet of the connection.

**NOTE:** *Die stamping is prohibited by API Spec 5CT Group 2 products.*

**b. SEQUENCE:**

1. API Monogram (  $\Phi$  ).

2. Specification and process designation, see Section 3, Ex.: 15LT-A for process A.

When applicable the API License number shall be applied in lieu of 15 LT.

3. Date of Manufacture, month and year, ex.: Jan 93 = 1/93

4. Unique manufacturers lot identification number.

Example: Tubulars lined by process A on January 1993 should be marked as follows:

$\Phi$  15LT-A-1/93-(ID#)

Example: Tubulars lined by a Licensee issued License number 15LT0001 and using process A on January 1993 should be marked as follows:

$\Phi$  15LT0001-A-1/93-(ID#)

**APPENDIX C  
REFERENCE STANDARDS**

<b>Designation</b>	<b>Title</b>	<b>Applicable Revision</b>
API Spec 5CT	Specification for Casing & Tubing	11/01/92
API Spec 5L	Specification for Line Pipe	5/01/90
API RP 5L7	Recommended Practices for Unprimed Internal Fusion Bonded Epoxy Coating of Line Pipe	6/30/88
ASTM D-1784	Standard Specification for Rigid Poly (Vinyl Chloride) (PVC) Compounds and Chlorinated Poly (Vinyl Chloride) (CPVC) Compounds	1981
ASTM D-2241	Standard Specification for Poly (Vinyl Chloride) (PVC) Pressure-rated Pipe (SDR series)	1987
ASTM D-2855	Standard Practice for Making Solvent- Cemented Joints with Poly (Vinyl Chloride) (PVC) Pipe and Fittings	1983
ASTM D-792	Specific Gravity and Density of Plastics by Displacement	1966
ASTM D-2152	Test Method for Degree of Fusion of Extruded Poly (Vinyl Chloride) (PVC) Pipe and Molded Fittings by Acetone Immersion	1980
ASTM D-2444	Test Method for Impact Resistance of Thermoplastic Pipe and Fittings by means of a Tup (falling weight)	1984
ASTM D-883	Standard Definitions of Terms Relating to Plastics	1983
NACE TMO170-70	Visual Standard for Surfaces of New Steel Airblast Cleaned with Sand Abrasive	1970

## APPENDIX D METRIC CONVERSIONS

A decimal/inch system is the standard for the dimensions shown in this Specification.

### LENGTH

1 inch (in.) = 25.4 millimetres (mm) exactly

### PRESSURE

1 pound per square inch (psi) = 0.06894757 Bar

NOTE: 1 Bar = 100 kilopascals (kPa)

### STRENGTH OR STRESS

1 pound per square inch (psi) = 0.006894757 Megapascals (MPa)

### IMPACT ENERGY

1 foot-pound (ft-lb) = 1.3558181 Joules (J)

### TORQUE

1 foot-pound (ft-lb) = 1.3558181 newton-metres (N m)

### TEMPERATURE

The following formula was used to convert degrees Fahrenheit (°F) to degrees Celsius (°C)

$$^{\circ}\text{C} = 5/9 (\text{F}-32)$$

### MASS

1 pound (lb) = 0.4535924 kilograms (kg)



## APPENDIX E PURCHASER INSPECTION

**a. INSPECTION NOTICE.** Where the inspector representing the purchaser desires to inspect this pipe or witness quality control tests, reasonable notice shall be given of the time at which the product is to be manufactured.

**b. PLANT ACCESS.** The inspector representing the purchaser shall have ready access at all times, while work on the contract of the Purchaser is being performed, to all parts of the Manufacturer's facility which will concern the product ordered. The Manufacturer shall afford the Inspector all reasonable and safe facilities to satisfy him

that the product is being manufactured in accordance with this specification. All inspections should be made at the place of manufacture prior to shipment, unless otherwise specified on the purchase order, and shall be so conducted as not to interfere unnecessarily with the operation of the facility.

**c. ACCEPTANCE.** The purchase order may require, if agreed upon by manufacturer and purchaser, that written acceptance be required from purchaser's inspectors for each lot prior to shipment.

**Order No. 811-07228**

**Additional copies available from**  
**AMERICAN PETROLEUM INSTITUTE**  
Publications and Distribution Section  
1220 L Street, NW  
Washington, DC 20005  
(202) 682-8375

